



Binder for cement-based grouts

- For mixing into cement-based grouts
- Increases mechanical wear resistance, flexibility and adhesiveness of the grout
- Reduces the capillary absorption capacity of the grout
- Improves the grout's resistance to detergents and hard water
- For interior and exterior use

Product

Polymer dispersion

Usage

Joint type	Dry rooms	Wet rooms	Outdoors	Joint binder use	Usage Litres per kg of powder
Use					
Alfix UniversalFuge CeraFill 10	X	X	X	Undiluted	Approx. 0.20
Alfix UniversalFuge CeraFill 18	X	X	X	Undiluted	Approx. 0.18
Alfix UniversalFuge CeraFill 20	X	X	X	Undiluted	Approx. 0.18
Alfix FineFuge CeraFill 5	X	X	-	Undiluted	Approx. 0.24
Alfix QuickFuge 8 Premium	X	X	-	Undiluted	Approx. 0.21

Packaging

10 litre plastic container.

General

The joints must be clean of adhesive and loose particles and have a uniform depth before starting work. Adding Alfix JointBinder to the grout can, depending on the type of tile - e.g. matt, non-slip or open surfaces - make it extra difficult to remove any grout residue.

Instructions for use

Stir undiluted Alfix JointBinder into the grout until the desired consistency is achieved. Only use Alfix JointBinder to adjust the consistency of the grout.

Pour Alfix JointBinder into a clean container and add the powder gradually while stirring vigorously to produce a smooth, lump-free paste. Stir until a homogeneous, lump-free consistency is achieved.

After a few minutes resting time, stir the grout thoroughly again before use.

Before applying the grout, wipe the tiles with a damp sponge. Apply the sealant with a grouting float diagonally across the joints, pressing it down and filling the joints completely. Once the grout is beginning to set, clean the surface using a well-wrung sponge; rinse the sponge regularly with clean water. Start by working diagonally until the joints are neat and even. Finish off with a final wipe of the surface with a well-wrung sponge. Limit the area to be grouted to avoid the grout setting on the tile surface.

To ensure optimal performance, it is important to keep the joints moist for the first few days after grouting.

Cleaning

Clean tools in water before the grout with JointBinder dries. Dried JointBinder is removed mechanically or with a solvent such as acetone.

It is recommended to wear protective gloves while working as the product adheres strongly to skin.

Tests

EMICODE test defined by GEV, Gemeinschaft Emissionkontrollierte Verlegestoffe [Association for the Control of Emissions in Products for Flooring Installation, Adhesives and Building Materials].

References

Product information for:

- Alfix FineFuge CeraFill 5
- Alfix QuickFuge Premium 8
- Alfix UniversalFuge CeraFill 10
- Alfix IndustryFuge CeraFill 18
- Alfix RustiqFuge CeraFill 20

Material safety data sheet

If you have any doubts or questions, contact our Technical Service department.
For the most recently updated version of this data sheet, go to alfix.com

Technical data

Working temperature

Min. +10°C

Density

Approx. 1.0 kg/litre

Storage

Approx. 12 months frost-free in unopened packaging